



## ACID#8 AEROSOL

### Ready to Use Etch Primer

<b>Description</b>	<p><b>ACID #8</b> is a 1K ready to use etch primer available in aerosol cans. It is used for priming bare metal surfaces, this promotes adhesion of paint and prevents steel from rusting.</p> <p><b>ACID #8</b> is chromate free. Typical applications are over rub through areas prior to painting, on new bare metal panels or over bare seams before sealant is applied.</p>
<b>Surface preparation and instructions for use</b>	<p><b>ACID #8</b> can be applied to the following surfaces:-</p> <ul style="list-style-type: none"><li>• Bare steel.</li><li>• Aluminium.</li><li>• Galvanized and Zinc coated steels.</li><li>• Fully cured paint.</li><li>• Polyester bodyfillers and G.R.P.</li></ul> <p>Degrease with Precleaner or panel prep and allow to dry. E.g. S2000, S2001 or S2002. Abrade with 280-320 abrasive. Re-clean, dry and degrease.</p>
<b>Health and Safety Statement</b>	<p>FOR PROFESSIONAL USE ONLY. Read full instructions before use.</p> <p>IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at <a href="http://WWW.U-POL.COM">WWW.U-POL.COM</a>. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.</p>
<b>Application and Storage information</b>	<p>Shake can thoroughly before use for a minimum of 2 minutes.</p> <p>Apply 1-2 light even coats.</p> <p>Allow 3-5 minutes flash off time between coats.</p>
<b>Drying Time</b>	<p>Allow 10-20 minutes before overcoating.</p> <p>Drying time is dependent upon film thickness, humidity and temperature</p>
<b>Overpainting</b>	<p>Under normal circumstances it is not necessary to flat <b>ACID #8</b> and can be directly overcoated.</p> <p><b>ACID #8</b> may be overcoated directly with top coat.</p> <p>However, if the repair requires additional build primer filler should be used before topcoat is applied.</p>
<b>VOC information</b>	<p>For aerosols the EU limit for this product (product category: IIBe) in ready to use form is 840g/litre.</p> <p>For aerosols the VOC content of this product in ready to use form is 680g/litre</p>

U-POL LTD, 4TH FLOOR, THE GRANGE, 100 HIGH STREET, LONDON N14 6BN, UK  
Home Sales T: +44(0)20 8492 5920; F:+44(0)20 8181 6911; E: [uk.sales@u-pol.com](mailto:uk.sales@u-pol.com);  
Export Sales T: +44(0)20 8492 5900; F:+44(0)20 8150 5605; E: [sales@u-pol.com](mailto:sales@u-pol.com);  
Technical T: +44(0)1933 230 310; F:+44(0)1933 425 797; E: [technicaldepartment@u-pol.com](mailto:technicaldepartment@u-pol.com);  
[WWW.U-POL.COM](http://WWW.U-POL.COM)