




U-POL®

334 FINE FINISHING COMPOUND

Description	<p>U-POL 334 Fine Finishing Compound is a finer liquid abrasive designed to rectify modern paintwork to a high gloss finish. The carefully selected abrasives will rapidly remove P2000 grit or finer abrasive marks, restore dull oxidized paintwork and blend in dry edges of a repair. This formulation is suitable for all finishes including more difficult dark colours. It is water miscible and free from both silicone and ammonia.</p> <div data-bbox="539 521 639 790"></div> <div data-bbox="711 633 995 725"></div> <div data-bbox="1114 633 1401 725"></div>
Preparation	<p>Old paintwork should be cleaned thoroughly to remove road traffic film and dirt. Wipe down surface with System 2000, 2001 or 2002 degreaser.</p> <p>New paint should be fully cured in accordance with paint manufacturers' drying schedule. Minor orange peel, runs, scratches and dirt nibs should be removed using U-POL Maximum Film-backed ABD7/VP1500 P1500 grit abrasive disc or finer. Use of a soft interface pad is recommended to further refine the scratch pattern. Remove sanding debris from surface with U-POL Tack Cloth and degrease.</p> <p>If any rubber trim or panel seams are likely to become dirty during compounding, spray a light coat of water onto the exposed surfaces, this will make cleaning up easy.</p>
Application	<p>Use with either a U-POL Firm Compounding Foam Mop or a Soft Polishing Foam Mop depending on the degree of cutting action required. Ensure the mop is clean and free from dust and dirt which may scratch paint surface. Soak the mop in clean water then squeeze out any excessive water. Fit mop to a polishing machine and spin off to remove any excess water.</p> <p>Shake U-POL 334 before use. Working a small area at a time, apply product to mop or directly to panel and spread over the area using the foam pad. Begin compounding at buffer speed of 1200-1500 RPM and medium pressure; always start polisher with the mop head flat on the surface. Reduce speed and/or pressure when compounding panel edges or ridges. Gradually decrease the pressure and buff until desired finish is achieved. More compound and/or water can be added if required. Wipe clean using a U-POL Micro Fibre Polishing Cloth. Clean mop heads regularly to avoid build-up of paint that may impair future work.</p> <p>U-POL 334 may also be applied by hand with a soft polishing cloth using a buffing action. Do not use cotton or mutton cloths as these are too coarse and can scratch surface.</p>
Additional Information	<p>The finish can be further enhanced using 335 High Gloss Final Glaze and/or 336 Ultra Gloss Wax Protector from the U-POL Automotive Polishing System. Other products in the system are U-POL 333 Cutting Compound where a more aggressive cutting action is required, available in paste or liquid form. All products are 100% bodyshop safe.</p>
Order Code	QW334/1 - 1 litre bottle (6 units per carton)
Storage	It is recommended that U-POL 334 is stored in a frost free environment.

U-POL®

Tools	<p><u>By Machine:</u> QWMS - Soft Polishing Foam Mop (Fast Fix or Backing Plate) for a high gloss immaculate finish on dark colours. QWMF - Firm Compounding Foam Mop (Fast Fix or Backing Plate) for faster results on hard aged, ceramic and scratch resistant coatings.</p> <p><u>By Hand:</u> QWCMF - Micro Fibre Polishing Cloth</p>
Health and Safety Statement	FOR PROFESSIONAL USE ONLY. Read full instructions before use. U-POL disclaim any liability where the end user does not wear the recommended personal protective equipment.
VOC Information	VOC content 258g/l

U-POL LTD, 4TH FLOOR, THE GRANGE, 100 HIGH STREET, LONDON N14 6BN, UK
Home Sales T: +44(0)20 8492 5920; F:+44(0)20 8181 6911; E: uk.sales@u-pol.com;
Export Sales T: +44(0)20 8492 5900; F:+44(0)20 8150 5605; E: sales@u-pol.com;
Technical T: +44(0)1933 230 310; F:+44(0)1933 425 797; E: technicaldepartment@u-pol.com;
WWW.U-POL.COM